

Daricco "Travertino F" – це фасадна акрилова декоративна штукатурка посилена силоксаном на основі натурального меленого мармуру, за допомогою якої можна імітувати натуральні покриття з матовою структурою: **імітація травертина, черепашника, ефект бетону, ефект скелі** а також створювати різноманітні рельєфні структури в поєднанні з іншими типами декоративних штукатурок. Розмір зерна 0,5 мм.

Склад:

Мінеральні наповнювачі, мармурова крихта, водна акрилова дисперсія, гідрофобізатори, реологічні добавки.

Особливості:

- Штукатурка дає змогу створити повну імітацію каменю травертина; скелі.
- Продукт можна використовувати на фасадах будівель та у вологих приміщеннях.
- Відмінно протистоїть атмосферним опадам та дії УФ.
- Travertino стійкий до перепадів температури.
- Стійка до механічних пошкоджень і стирання.
- Покриття легко реставрується.
- Не вимагає ідеальної підготовки основи та чудово маскує дрібні дефекти.

Основа:

На фасадах будівель найкращою основою для нанесення **"Travertino F"** є пінопласт армований сіткою та оброблений цементно-піщаною армуючою сумішшю преміальної марки. Поверхня повинна бути чистою, **сухою** без тріщин та придатною для обробки. Свіжі цементно-піщані штукатурки або шпаклівки мають бути витримані згідно рекомендацій виробника. Нерівності вирівняти цементною шпаклівкою. Уражені грибками місця очистити та обробити антисептичним розчином.

Спосіб нанесення та виконання робіт:

Для нанесення штукатурки **«Travertino F»** необхідні такі інструменти: кельма з нержавіючої сталі та шпатель, а також допоміжні щітки та структурні валики. Малюнок можна наносити в один або кілька шарів залежно від обраного типу покриття.

Наносити штукатурку треба від кута до кута стіни без зупинок. На фасадах слід уникати прямих сонячних променів, вітряної погоди або нанесення штукатурки на стіну нагріту сонцем. Також не слід наносити штукатурку в дощову погоду. Найкраща температура для нанесення (від +18 до +25С).

Характерний вигляд каменю матеріал набуває після часткового підсихання й «ущільнення» його за допомогою кельми. Витрата один шар 0,7-0,8 кг./м² залежно від основи. Час висихання шару 12-24 години. Всі рекомендації ефективні при температурі основи +20 С та відносній вологості повітря 60%, в інших умовах терміни висихання та витримки можуть змінитися. Інструмент промити водою відразу після закінчення робіт.

Заходи безпеки та утилізація:

Зберігати у недоступному для дітей місці. При попаданні в очі одразу промити їх чистою водою. Залишки висохлої штукатурки екологічно безпечні і є звичайним будівельним сміттям.

Зберігання:

У щільно закритій тарі в прохолодному місці при температурі від +5 до +30 С. Слід уникати потрапляння прямих сонячних променів на тару. Гарантійний термін зберігання в герметично закритій упаковці - 12 місяців.

Технічні характеристики:

Сфера застосування: стіни, стелі всередині та ззовні приміщень

Способи нанесення: Кельма, шпатель, щітки

Розріджувач: вода до 5%

Температура нанесення: Мін. +12 °С.

Витрата: 0,7-0,8 кг./м²(в один шар)

Колір: сірувато-білий

Час висихання: 12-24 години

Очищення інструменту: вода

Блиск: Матовий

Термін зберігання: 12 міс.

Виробник: : ТОВ «Дарико ЛТД» Україна, м Київ, вул. Алматинська 8,

Travertino F

Daricco "Travertino F" is a facade acrylic decorative plaster reinforced with siloxane based on natural ground marble, which can be used to imitate natural coatings with a matte structure: imitation of travertine, shell rock, concrete effect, rock effect, as well as to create various relief structures in combination with other types of decorative plasters. The grain size is 0.5 mm.

Composition:

Mineral fillers, marble chips, aqueous acrylic dispersion, water repellents, rheological additives.

Features:

- The plaster allows you to create a complete imitation of travertine stone; rock.
- The product can be used on building facades and in wet rooms.
- It perfectly resists atmospheric precipitation and UV exposure.
- Travertino is resistant to temperature changes.
- It is resistant to mechanical damage and abrasion.
- The coating is easy to restore.
- It does not require perfect preparation of the base and perfectly masks minor defects.

Substrate:

On building facades, the best substrate for applying Travertino F is mesh-reinforced styrofoam treated with a premium cement-sand putty. The surface must be clean, dry, crack-free and suitable for processing. Freshly applied cement-sand plasters or putties shall be cured according to the manufacturer's recommendations. Level out unevenness with cement putty. Clean and treat the areas affected by fungi with an antiseptic solution.

Method of application and work performance:

To apply Travertino F plaster, the following tools are required: a stainless steel trowel and a spatula, as well as auxiliary brushes and structural rollers. The coating can be applied in one or several layers depending on the type of coating chosen. Apply the plaster from corner to corner of the wall without stopping. On facades, avoid direct sunlight, windy weather or applying plaster to a wall heated by the sun. Also, do not apply the plaster in rainy weather. The best temperature for application is from +18 to +25C.

The material acquires the characteristic appearance of stone after partial drying and "compacting" it with a trowel. Consumption of one layer is 0.7-0.8 kg/m² depending on the base. Drying time of the layer is 12-24 hours. All recommendations are effective at a base temperature of +20°C and relative humidity of 60%, in other conditions the drying and curing time may vary. Rinse the tool with water immediately after finishing the work.

Precautions for use and disposal:

Keep out of the reach of children. In case of contact with eyes, rinse immediately with clean water. Residues of dried plaster are environmentally safe and are normal construction waste.

Storage:

In a tightly closed container in a cool place at a temperature from +5 to +30 C. Avoid direct sunlight on the container. The guaranteed shelf life in a hermetically sealed package is 12 months.

Technical characteristics:

Application area: walls, ceilings indoors and outdoors

Application methods: Trowel, spatula, brushes

Thinning agent: water up to 5%.

Application temperature: Min. +12 °C.

Consumption: 0.7-0.8 kg/m² (in one layer)

Color: grayish-white

Drying time: 12-24 hours

Tool cleaning: water

Gloss: Matte

Shelf life: 12 months.

Manufacturer: : LLC " Daricco LTD " Ukraine, Kyiv, Almatyinskaya str. 8,